*Thesis submitted to fulfill the requirements for the degree of 'Doctor in Health Sciences'* 

#### Promotor

Prof. dr. Heidi Declercq Ghent University, Belgium KU Leuven, Belgium

#### Guidance committee

Prof. dr. Anne Vral Ghent University, Belgium

Prof. dr. Peter Dubruel Ghent University, Belgium

#### Examination committee

Prof. dr. Jolanda van Hengel (chair) Ghent University, Belgium

Prof. dr. apr. Olivier De Wever Ghent University, Belgium

Prof. dr. Ward De Spiegelaere Ghent University, Belgium

dr. Jasper Van Hoorick Ghent University, Belgium

Prof. dr. Veerle Bloemen KU Leuven, Belgium

Prof. dr. ir. Jeroen Rouwkema University of Twente, Netherlands



# Contact

Department of Human Structure and Repair Tissue Engineering and Biomaterials Group

Lise.DeMoor@ugent.be T +32 9 332 34 47 https://www.ugent.be/ge/hsr

The manuscript can be requested by email



### **Biofabrication**

of soft and vascularized tissues by bioprinting

Lise De Moor May 20<sup>th</sup>, 2021



### Summary

Tissue engineering (TE), is an interdisciplinary research field, combining the principles of engineering and life sciences towards the development of bioartificial tissue substitutes to restore, replace, or improve the function of damaged biological tissues or whole organs. The rise of biofabrication techniques, such as three-dimensional (3D) bioprinting, has a great impact on the field because it enables tissue engineers to mimic the 3D configuration of the native tissue by the precise layer-bylayer placement of several cell types and biomaterials along multiple axes with high spatial control.

In this dissertation, we tackle the TE of two extremes, vascularized tissue versus avascular cartilage tissue, by pursuing the same biofabrication strategy and workflow: hybrid bioprinting. First, cellular spheroids are formed (figure A). These are very small 3D tissues that are used as biological building blocks. To form a bioink, the spheroids are combined with a hydrogel, a methacrylamide-modified gelatin (gelMA, figure B), which functions as a supporting material, entrapping the spheroids while printing. This bioink can then be processed by extrusion bioprinting (figure C) to create a 3D tissue construct, mimicking the properties of the tissue of origin.



**Cartilages** within the knee joint are prone to injury because of the high mechanical stress the knee joint withstands on a daily basis. Therefore, TE strategies are pursued in order to develop new regenerative therapies. To generate fibro- or hyaline cartilage, porcine fibrochondrocyte (FC) and articular chondrocyte (AC) spheroids were formed using agarose microwells, and redifferentiation was further induced by culture in chondrogenic medium and a low oxygen tension environment. Only AC redifferentiated into 3D cartilage spheroids displaying an aggrecan and collagen type II-rich extracellular matrix, suggesting that AC are a suitable cell type for articular cartilage engineering. When the spheroids are combined with gelMA, hydrogel intrinsic cues can deeply affect cell fate and to date the influence of hydrogel encapsulation on the viability and the phenotype of spheroids is hardly described. To investigate the influence of gelMA encapsulation on cartilage spheroids, different maturation stages of AC spheroids (3-, 7- or 14-day-old) were combined with various concentrations of gelMA (10, 15 and 20 w/v%) with Irgacure 2959 as a photo-initiator (PI). Overall, increasing the gelMA concentration, and thus increasing hydrogel stiffness, is associated with a decrease in collagen type II and an increase in collagen type I. Departing from the same AC cell source, different cartilage phenotypes could be induced by varying these parameters. To enhance clinical translation, this workflow was also tested with human bone marrow-derived mesenchymal stem cells.

The key challenge in the biofabrication of biologically functional products remains the integration of a vascular tree. Especially the creation of **microvasculature** of the small micron range (< 10  $\mu$ m) remains challenging due to the limited resolution of most bioprinting techniques. To address this shortcoming in a biologydriven way, we developed prevascularized spheroids that can be incorporated throughout the bioprinted construct as capillarycontaining building blocks. Human umbilical vein endothelial cells (HUVEC) were cocultured with human foreskin fibroblasts (HFF) and adipose tissue-derived mesenchymal stem cells (ADSC) as supporting cells. By balancing several parameters such as the cell number per spheroid, different cell type combinations and the applied cell ratio, HUVEC/HFF/ADSC small diameter spheroids wherein HUVEC spontaneously self-organized in a capillary-like network were generated. When encapsulated in 10 w/v% gelMA, HUVEC were able to sprout throughout the hydrogel. Post extrusion printing, the photocrosslinking conditions affected the angiogenic potential of the spheroids.

In conclusion, for spheroid generation, the agarose microwell system proved to be suitable for the formation of both cartilage and prevascularized spheroids with small diameters compatible for deposition by the print needle. GelMA is a promising material to function as the biomaterial component of the spheroid-laden bioink as it exhibits favorable properties in terms of printability and it supports spheroid viability, the chondrogenic phenotype of the cartilage spheroids. The maturation stage of the spheroids before encapsulation proved to be important to achieve the desired phenotype, especially for the cartilage spheroids. Finally, the spheroid-laden bioinks proved to be printable and the gelMA concentration, type of PI, and post printing photo-crosslinking conditions can affect the spheroid functionality, and the spheroid phenotype.

## Curriculum Vitae

| <u>Education</u>                 | Ghent University  |
|----------------------------------|---|
| 2015 – 2021                      | PhD in Health Sciences<br>Tissue Engineering & Biomaterials Group   |
| 2013 - 2015                      | Master of Science in Biomedical Sciences  |
| 2009 - 2013                      | Bachelor of Science in Biomedical Sciences  |
|                                  |   |
| <u>Experience</u>                | Ghent University  |
| <u>Experience</u><br>2015 – 2021 | Ghent University<br>PhD candidate<br><i>Biofabrication of cartilage &amp; vascular tissues</i>  |
| <u>Experience</u><br>2015 – 2021 | Ghent University<br>PhD candidate<br><i>Biofabrication of cartilage &amp; vascular tissues</i><br>Teaching assistant<br><i>Basic and Systematic Histology, Cell culture</i> |

### **Publications**

<u>De Moor L</u>, Merovci I, Baetens S, Verstraeten J, Kowalska P, Krysko D V, De Vos W H, Declercq H. High-throughput fabrication of vascularized spheroids for bioprinting. Biofabrication 2018; 10,035009.

<u>De Moor L</u>, Beyls E, Declercq H. Scaffold free microtissue formation for enhanced cartilage repair. Ann. Biomed. Eng. 2020; 48, 298–311.

<u>De Moor L</u>, Fernandez S, Vercruysse C, Tytgat L, Asadian M, De Geyter N, Van Vlierberghe S, Dubruel P, Declercq H. Hybrid bioprinting of chondrogenically induced human mesenchymal stem cell spheroids. Front. Bioeng.. Biotechnol. 2020; 8, 484.

<u>De Moor L</u>, Minne M, Tytgat L, Vercruysse C, Dubruel P, Van Vlierberghe S, Declercq H. Tuning the phenotype of cartilage tissue mimics by varying spheroid maturation and methacrylamide-modified gelatin hydrogel characteristics. Macromol. Biosci. 2021; 3, 2000401.

<u>De Moor L</u>, Smet J, Plovyt M, Bekaert B, Vercruysse C, Asadian M, De Geyter N, Van Vlierberghe S, Dubruel P, Declercq H. Engineering microvasculature by 3D bioprinting of prevascularized spheroids in photo-crosslinkable gelatin. In prep.